

## Acoustics - Water-borne noise-damping coating

Description A one-component water-borne, functional, noise-

damping coating for airless application.

Product features Suitable to be used on interior and sheltered surfaces

only.

Recommended uses Recommended to be used on steel roofing sheets,

metal surfaces in vehicles and railway cars, ventilation ducts and other metal surfaces where vibration and

noise problem occurs.



TECHNICAL DATA

KULTAVA HIMMEA GLOSS MATT H. 1.1 m²/l m²/l m²/l

Features Excellent acoustic damping and vibration absorbing properties.

Forms very elastic and porous coating layer.

Prevents from condensation.

Complies with the requirements of EN13501-1, class A2-s1d0.

Colour Range White and grey.

Gloss grade Matt

Coverage

Recommended film thickness		Theoretical coverage
dry	wet	
600 g/m <sup>2</sup>	1200 g/m <sup>2</sup>	1,1 m <sup>2</sup> /l
450 μm	900 μm	
1800 g/m <sup>2</sup>	3600 g/m <sup>2</sup>	0,4 m <sup>2</sup> /l
1350 μm	2700 μm	

Practical coverage depends on the application method, painting conditions and

the shape and roughness of the surface to be coated.

Can sizes 18 I, 100 I.

Thinner Water

Drying times

Application method By airless spray or when not possible by brush or roller.

Through dry	+20°C / RH 55%	+50°C, kiertoilma
WFT 1200 g/m <sup>2</sup>	8–10 h	4 h

Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation.

Special feature Noise damping: Tan Delta (combined) 0,116 (VTT-CR-00259-15, test report



## Acoustics - Water-borne noise-damping coating

available on request)

Solids volume 50%.

Density 1.3 kg/l

Product code 006 5129, 006 5130

## APPLICATION DETAILS

Application conditions

Preparation

Priming

All surfaces must be dry. The temperature of the ambient air and surface should not fall below  $\pm 10^{\circ}$ C during application and drying. Relative humidity should not exceed 80%. The surface temperature of the steel should remain at least 3°C above the dew point.

The temperature of paint itself should be above +15°C for proper application. Good ventilation is required in confined areas during application and drying.

Oil, grease, salts and dirt are removed by appropriate means. (ISO 12944-4)

Aluminium surfaces: Sweep blast-clean with non-metallic abrasives to an even roughness. (SaS, SFS 5873) If sweep blasting is not possible, the surface should be roughened by hand abrading or washed with MAALIPESU detergent.

Zinc and aluzinc surfaces: Sweep blast-clean with mineral abrasives, e.g. quartz sand, to an even roughness. (SaS, SFS 5873) If sweep blasting is not possible, the surface should be roughened by hand abrading or washed with PANSSARIPESU detergent.

Primed surfaces: Industrial coil primer on the backside of the steel roofing sheets does not require any special preparation. Oil, grease, salt and dirt are removed from the surface by appropriate means. Repair any damage to the primer coat with Temaprime EE or Rostex Super. Note the overcoating time of primer. (ISO 12944-4)

Stainless steel: Roughen the surface by grinding of sweep blasting using non-

metallic abrasives.

Temaprime EE, Temacoat RM 40, Temacoat Primer, Temacoat GPL-S Primer,

Rostex Super Akva and Rostex Super or directly on galvanized surface. Old

painted surfaces are recommended to roughen to ensure adhesion.

Application By airless spray or when not possible by brush or roller. Mix the paint thoroughly

before use. The paint can be thinned 0-5% by volume if necessary. Spray nozzle

tip 0.035"-0.039" and nozzle pressure 150-180 bar.

Finishing Do not overcoat with any other type of coating as it causes loss of condensation

protection properties.

EU VOC 2004/42/EC-limit value

The Volatile Organic Compounds amount is 15 g/litre of paint mixture.

HEALTH AND SAFETY LABELLING according to Regulation (EC) No. 1272/2008

-



## Acoustics - Water-borne noise-damping coating

Safety data sheet

ENVIRONMENTAL and WASTE DISPOSAL

Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets. A health and safety data sheet is available on request from Tikkurila Oyj. Only for industrial and professional use.

**TRANSPORT** 

\_