

# TEKNOPOX PRIMER 9-00

## Epoxy Primer

<b>PAINT TYPE</b>	Two-pack epoxy primer.
<b>USAGE</b>	Used as an anticorrosive paint on blast-cleaned steel surfaces as well as on zinc coated and aluminium surfaces in objects where good resistance to abrasion, water, oil and chemicals is required.
<b>SPECIAL PROPERTIES</b>	Paint is fast drying, has good application properties and levelling is also good. Will cure even at +0°C temperature.

**TECHNICAL DATA**

<b>Mixing ratio</b>	Base (Comp. A): Hardener (Comp B): TEKNOPOX HARDENER 7219	7 parts by volume 1 part by volume	
<b>Pot life, +23 °C</b>	3 h		
<b>Solids</b>	62 ±2% by volume		
<b>Total mass of solids</b>	abt. 1030 g/l		
<b>Volatile organic compound (VOC)</b>	abt. 350 g/l		
<b>Recommended film thickness and theoretical spreading rate</b>	Dry film (µm)	Wet film (µm)	Theoretical spreading rate (m <sup>2</sup> /l)
	60	97	10,3
	80	129	7,8
	100	161	6,2
	120	193	5,2

As many of the paint's properties will change if too thick coats are applied, it is not recommended that the product is applied to a film thickness that is more than double of the thickest recommended film.

**Practical spreading rate** The values depend on the application technique, surface conditions, overspray, etc.

**Drying time, +23°C / 50% RH (dry film 60 µm)**

- dust free (ISO 9117-3:2010) after 10 min  
 - touch dry (ISO 9117-5:2012) after 45 min

**Overcoatable, 50% RH (dry film 60 µm)**

surface temperature	by itself		with TEKNODUR 0050, TEKNODUR COMBI 340-811 and TEKNODUR COMBI 3430 polyurethane paints		with TEKNODUR COMBI 3560-78		with TEKNODUR 100 9-12	
	min.	max. *	min.	max. *	min.	max. *	min.	max. *
<b>+10°C</b>	after 1 h	after 2 months	after 1 h	after 1 month	after 1 h	after 2 months	after 1 h	after 14 d
<b>+23°C</b>	after 45 min	after 2 months	after 45 min	after 1 month	after 45 min	after 2 months	after 45 min	after 14 d

\*Maximum overcoating interval without roughening.

Increase in film thickness and rise in the relative humidity of the air in the drying space usually slow down the drying process.

<b>Thinner, clean up</b>	TEKNOSOLV 9506
<b>Finish</b>	Semi-matt
<b>Colours</b>	White, light grey ~ RAL-7035, Buff ~ RAL-1014
<b>SAFETY MARKINGS</b>	See Safety Data Sheet.

PTO

**DIRECTION FOR USE****Surface preparation**

Remove from the surfaces any contaminants that might be detrimental to surface preparation and painting. Remove also water-soluble salts by using appropriate methods. The surfaces are prepared according to the different materials as follows:

**STEEL SURFACES:** Remove mill scale and rust by blast cleaning to preparation grade Sa 2½ (standard ISO 8501-1). Roughening the surface of thin-plate improves the adhesion of the paint to the substrate.

**ZINC SURFACES:** Hot-dip-galvanized steel structures that are exposed to atmospheric corrosion can be painted if the surfaces are sweep blast-cleaned (SaS) till matt all over. Suitable cleaning agents are, e.g. aluminium oxide and natural sand. It is not recommended according to standard ISO 12944-5 to paint hot-dip-galvanized objects that are subjected to immersion strain. Painting of hot-dip-galvanized objects that are subjected to immersion strain must be discussed separately with Teknos.

It is recommended that new zinc-coated thin-plate structures are treated with sweep blast-cleaning (SaS). Surfaces that have been weathered to matt can be treated also with RENSA STEEL washing agent for galvanized surfaces.

**ALUMINIUM SURFACES:** Treat the surfaces with RENSA STEEL washing agent for galvanized surfaces. Surfaces that are exposed to weathering are also roughened up with sweep blast-cleaning (AlSaS) or sanding.

**OLD PAINTED SURFACES SUITABLE FOR OVERCOATING:** Any impurities that might be detrimental to the application of paint (e.g. grease and salts) are removed. The surfaces must be dry and clean. Old, painted surfaces that have exceeded the maximum overcoating time are to be roughened as well. Damaged parts are prepared in accordance with the requirements of the substrate and the maintenance coating.

The place and time of the preparation are to be chosen so that the prepared surface will not get dirty or damp before the subsequent treatment.

**Mixing of the components**

Take into consideration the pot life of the mixture when estimating the amount to be mixed at a time. Before painting the base and hardener are mixed in right proportion. Stir thoroughly down to the bottom of the vessel. Inadequate stirring or incorrect mixing ratio results in imperfect curing and impaired film properties.

**Application conditions**

The surface to be painted must be dry. The temperature of the ambient air, the surface and the paint shall be above 0°C and the relative air humidity below 80% during the application and drying period. Additionally the temperature of the surface to be painted and the paint must be at least 3°C above the dew point of the ambient air.

**Prefabrication primer**

KORRO E Epoxy Prefabrication Primer can be used, when required.

It is recommended that before top coating the surface is cleaned to quality grade FeX05, X = prefabrication primer (SFS 8145).

**Application**

Before use stir the paint thoroughly.

If needed, thin the paint with TEKNOSOLV 9506.

Apply preferably by airless spray as only this method provides the recommended film thickness in a single operation. Use airless spray nozzle 0.013 - 0.017". Brush can be used for touching up and painting small areas.

**ADDITIONAL INFORMATION**

The storage stability is shown on the label. Store in a cool place and in tightly closed containers.

Additional instructive information for surface preparation can be found in standards EN ISO 12944-4 and ISO 8501-2.

---

The information of this data sheet is normative and based on laboratory tests and practical experience. Teknos guarantees that the product quality conforms to our quality system. Teknos accepts, however, no liability for the actual application work, as this is to a great extent dependent on the conditions during handling and application. Teknos accepts no liability for any damage resulting from misapplication of the product. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos data sheets, material safety data sheets and system sheets are on our home pages [www.teknos.com](http://www.teknos.com).

---



EN\_2173\_Tuoteseloste.pdf